



Phone: (810) 326-1451 Fax: (586) 408-6363
 www.dynamicpolymer.com

Technical Data Sheet

DYN-PPC202 Black

Polypropylene Copolymer 20 Melt

| Typical Compound Properties | Value / Measure | | Test Methods |
|--------------------------------|-----------------|--------------|--------------|
| Physical Properties | | | |
| | English Units | Metric Units | |
| Density | 0.91 g/cm3 | 0.91 g/cm3 | ASTM D-792 |
| Melt Flow Rate @ 230° / 2.16kg | 20 g/10 min | | ASTM D-792 |
| Mechanical Properties | | | |
| Izod Impact - Notched | 2 ft-lb/in | 107 J/m | ASTM D-256 |
| Tensile Strength @ Yield | 3,100 psi | 21 MPa | ASTM D-638 |
| Flexural Modulus | 129,000 psi | 890 MPa | ASTM D-790 |
| Thermal Properties | | | |

All tests are performed on dry as molded ASTM test bars.

General Product Type Information

DYN-PPC202, is also available with internal and external lubricants, UV stabilized and other modifications. Manufactured with recycled content. Further information and details are available upon request.

Processing Information

| Temperatures | | F | C |
|--------------|--------|-----------|-----------|
| Barrel | Rear | 360 - 400 | 184 - 206 |
| | Center | 380 - 410 | 195 - 212 |
| | Front | 400 - 430 | 206 - 223 |
| | Nozzle | 400 - 430 | 206 - 223 |
| | Mold | 70 - 120 | 21 - 49 |

Drying

Type
 Temperature
 Time
 Max. % Moisture

The property values listed above have been obtained using laboratory controlled test methods. They are offered without guarantee since conditions under which the product is used are beyond our control. Therefore, Dynamic Polymer Solutions disclaims any liability for loss or damage incurred in connection with the use of this product. Optimum processing conditions will depend on such factors as machine size, screw design, part dimension, mold design, runner and gate design, and material residence time. These recommendations are intended only as a guide to achieve stable processing and good part quality.