



Phone: (810) 326-1451 Fax: (586) 408-6363
 www.dynamicpolymer.com

Technical Data Sheet

DYN-PPH30G Black

Polypropylene Homopolymer, Chemically Coupled, 30% Glass Fiber Reinforced

Typical Compound Properties	Value / Measure		Test Methods
Physical Properties			
	English Units	Metric Units	
Density	1.13 g/cm ³	1.13 g/cm ³	ASTM D-792
Melt Flow Rate @ 230° / 2.16kg	8 g/10 min		ASTM D-792
Ash Content	30 %	%	ASTM D-5630
Mechanical Properties			
Izod Impact - Notched	1.20 ft-lb/in	64 J/m	ASTM D-256
Tensile Strength @ Yield	8,800 psi	61 MPa	ASTM D-638
Tensile Elongation @ Break	9 %	9 %	ASTM D-638
Flexural Strength @ Yield	12,000 psi	83 MPa	ASTM D-790
Flexural Modulus	475,000 psi	3,277 MPa	ASTM D-790
Thermal Properties			
DTUL @ 66 psi (455 kPa)	291 Deg. F	145 Deg. C	ASTM D-648

All tests are performed on dry as molded ASTM test bars.

General Product Type Information

DYN-PPH30G, is also available with internal and external lubricants, UV stabilized and other modifications. Manufactured with recycled content. Further information and details are available upon request.

Processing Information

Temperatures		F	C
Barrel	Rear	380 - 400	217 - 228
	Center	390 - 410	223 - 234
	Front	400 - 420	228 - 240
	Nozzle	410 - 430	234 - 245
	Mold	120 - 150	27 - 66

Drying

Type
 Temperature
 Time
 Max. % Moisture

The property values listed above have been obtained using laboratory controlled test methods. They are offered without guarantee since conditions under which the product is used are beyond our control. Therefore, Dynamic Polymer Solutions disclaims any liability for loss or damage incurred in connection with the use of this product. Optimum processing conditions will depend on such factors as machine size, screw design, part dimension, mold design, runner and gate design, and material residence time. These recommendations are intended only as a guide to achieve stable processing and good part quality.